

PET-G 3D Filament

Material is specifically developed for 3D printing applications where easy processing and high toughness are crucial. The self-bonding ability will improve the strength and the durability of your creations

Material properties

| Description | Method | Typical value |
|------------------------------|------------------|------------------------|
| Density | ASTM D792 | 1.29 g/cm ³ |
| Glass transition temperature | ASTM D3418 | 80°C |
| Melting temperature | DSC | 180°C |
| Heat deflection temperature | ISO 75 (0.45MPa) | 68°C |
| Tensile strength at yield | ISO 527 | 46 MPa |

Printing properties

| | |
|----------------------|--|
| Hotend temperature | 245 -255°C |
| Heatbed temperature | 70 - 90°C |
| Cooling print object | 0 - 30% fan speed |
| Nozzle diameter | commonly used |
| Printing environment | open space or inside of box |
| Bed surface | commonly used (glassbed, PEI, steel etc..) |
| Bed adhesive | glue stick for easy removal |
| Drying | 6 - 8 hours at 65°C |

| Type of spool | Weight of empty spool |
|--------------------|-----------------------|
| 750 gr transparent | 230gr |
| 1 kg transparent | 250gr |
| 1 kg black | 220gr |
| 2,5kg black | 500gr |

www.aurapoi.com

carry any responsibility for injuries or any loss caused by using or AURAPOL material.